



# Jack Tar® Non-Skid Deck Compound 492-3

|                               |
|-------------------------------|
| <b>PRODUCT DESCRIPTION</b>    |
| <b>TYPICAL USES</b>           |
| <b>PRODUCT ADVANTAGES</b>     |
| <b>COLORS</b>                 |
| <b>PHYSICAL CONSTANTS</b>     |
| <b>APPLICATION</b>            |
| <b>SHIPPING &amp; STORAGE</b> |

**A high quality, specially selected and classified dry pumice stone for adding non-skid properties to paint.**

For industrial, commercial, marine and residential use in most deck or floor coatings to add a uniform rough texture to the finish, providing a safer, non-skid walking surface.

Jack Tar® Non-Skid Deck Compound can be easily added to almost any coating to provide a durable and uniform non-skid surface. Easily stirred into the coating. Unlike sand, this product does not settle rapidly and allows a more uniform distribution of the non-skid material in the finished coating. Uniform particle size for a better appearance. Very good abrasion resistance.

Minimal effect on original color of paint. (See "Limitations" on back page.)

**Nonvolatile -** By weight - 100%  
By volume - 100%

**VOC (Calculated) -** 0 lbs./gal.  
0 grams/liter

**Flash Point -** Does not flash

**Weight per gallon -** 18.4 lbs.

**Recommended addition -** 0.50 lbs per quart of paint  
1.75 lbs per gallon of paint

**Theoretical Coverage -** Apply coating at the normal recommended spreading rate.

**Method -** Brush or roll

**Thinner -** Use the recommended thinner for the paint.

**Dry time -** No effect on the drying time of the coating to which it is added

|                             |              |               |
|-----------------------------|--------------|---------------|
| <b>Consists of -</b>        | 1 Quart Unit | 1 Gallon Unit |
| <b>Unit Shipping Weight</b> | 1 lb         | 2 lbs.        |

**Shelf Life -** 24 months minimum from date of manufacture when maintained in protected storage @ 40-100°F (subject to reinspection thereafter).

## APPLICATION INSTRUCTIONS

Consult your Mobile Paint Representative for the protective coating system best suited for your requirements.

**Limitations:** All coatings should be applied in good weather when air and surface temperature are above 50°F and surface temperature is at least 5°F above the dew point. For optimum application properties, material should be between 70 to 100°F prior to mixing and application. Maintain unmixed material in closed containers in protected storage at 40 - 100°F. **NOTE:** This product is very light in color and has only a minimal effect on the color of the paint to which it is added. However, due to surface texture differences, the final appearance may differ from the paint without the Non-Skid Deck Compound. Evaluation should be done to determine whether the final appearance is acceptable.

**Surface Preparation:** Good surface preparation is essential to a satisfactory coating system. Remove all dirt, dust, oil, grease, mildew, rust, loose or cracked paint or other contamination. Follow surface preparation guidelines as recommended by the coating manufacturer.

**Compatibility:** This product is compatible with most paints available for use on surfaces which require non-skid properties. For specific recommendations concerning a particular type of coating, contact your Mobile Paint Representative for further information regarding compatibility. If doubt exists concerning compatibility of this product with the coating, mix a small amount of this product with the coating at the recommended mixing ratio and apply coating to a representative area (25 square feet minimum) and allow to cure and age several weeks. Then inspect for adhesion failure, wrinkling, lifting, blistering or any other sign of incompatibility. If there are no signs, coating work can proceed.

**Mixing:** This product is packaged in the proper amount for mixing with either a quart or gallon of paint. Suggested mixing ratio is ½ pound of Non-Skid Deck

Compound per quart of paint or 1¼ pounds per gallon of paint. This level is a starting point recommendation for an effective level of anti-skid properties. Either more or less of the compound may be used to reach your desired results. Always mix thoroughly with a power agitator to ensure that the product is uniformly mixed before application.

**Thinning:** Thin only with thinner recommended by the coating manufacturer.

**Application:** After mixing into the desired paint, apply by brush or roller. Spray application is not recommended due to the large particle size of the product. Apply at the spreading rate recommended by the coating manufacturer. For a more durable finish, a second coat of the same paint, without the addition of the Non-Skid Deck Compound, should be applied after the first coat is properly dry. Although best results are obtained by adding this material directly to the paint prior to application, Non-Skid Deck Compound may also be broadcast into freshly applied, wet paint for a non-skid finish. A second coat is also recommended if this technique is used.

**Safety:** Safe storage, handling and use dictate that adequate health and safety precautions be observed with this product and any paint it may be added to along with recommended thinner. User is specifically directed to consult the current Material Safety Data Sheet for this product as well as precautions contained on product labeling.

**Notice:** The technical data contained herein are true and accurate to the best of our knowledge. All products are offered and sold subject to Mobile Paint Manufacturing Company's Standard Conditions of Sale. Published technical data and instructions are subject to change without prior notice.

492-3(7/99)

### LIMITED WARRANTY

The successful performance of this product is highly dependent on many factors beyond our control. Results are highly dependent upon the skill of the operator. This product is manufactured to meet the highest level of consistency and quality for the intended use. Mobile Paint warrants that its products meet the specifications which it sets for them. Should this product be proven to be off-specification within one year from date of shipment, Mobile Paint will, at its sole discretion, either replace the product or issue credit for the original purchase price of the product. The replacement or refund shall be the buyer's sole remedy and Mobile Paint and its affiliates **MAKE NO OTHER WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY, DESIGN COMPATIBILITY AND FITNESS FOR A PARTICULAR PURPOSE. LABOR OR COST OF LABOR AND OTHER INCIDENTAL AND/OR CONSEQUENTIAL DAMAGES ARE SPECIFICALLY EXCLUDED.** The technical data contained herein are true and accurate to the best of our knowledge. Published technical data and instructions are subject to change without prior notice.